



**PRIMER PU-1000 - SINGLE-COMPONENT,
SOLVENT BASED, POLYURETHANE RESIN AS A
PRIMER**

PRIMER PU-1000 is a single component, low viscosity, high solids content polyurethane resin. It has been specifically designed to increase bonding and improve the surface leveling of the substrates prior to the application of the DESMOPOL or TECNOCOAT.

USES

Polyurethane resin to use in:

- it is specially designed to increase the adherence and improve planimetry of the substrates where will be applied DESMOPOL or TECNOCOAT waterproofing liquid system membranes.
- to apply in porous substrates such as concrete, mortar, or on plywood surfaces
- highly recommended as a bonding material on waterproofing membranes and PU resins repairs and overlaps work.

NOTE: call our technical department about the application to other supports or situations

density at 23°C	1,11 g/cm ³
adhesion on concrete	> 2 MPa
drying time at 23°C	±60 minutes
dilution	maximum: 5% DESMOSOLVENT



GENERAL FEATURES

- Single component polyurethane-based resin.
- It needs a flat, clean, and dry surface, as hard as possible.
- It can be applied on porous surfaces: concrete, cement, and on plywood
- It can be diluted in supports of low absorption.
- Depending on the state of the surface to be treated, unevenness, or plane level, the yield can vary between 100~200 g/m², in one or several thin layers. (do not apply thick coats)
- In applications on old, existing PUA and PU membranes or whatever with and smooth surface, the consumption will be between 50-100 g/m² (check "Repair and overlaps processes", in the Desmopol and Tecnocoat membranes' TDS)
- It can be applied with a roller, brush or airless spray equipment
- It can be applied on surfaces with a maximum surface humidity of 5%.
- Do not apply to surfaces that are damp or exuding water coming from the interior of the substrate (water pressure due to phreatic level, condensations, leaks, etc.).
- It can be applied in combination with mineral particles (silica sand) on very uneven surfaces.



- Translucent

PACKAGING

Metal tins of 5 kg and 20 kg.

SHELF LIFE

12 months for each product at temperatures between 5° C and 35° C, provided it is stored in a dry place. Once the tin has been opened, the product must be used immediately.

APPLICATION METHOD

- The surface must be clean and dry. If necessary, use pressure water to remove any oil or grease residue, efflorescence, or other contaminants, as well as loose cement laitance.
- In some cases, it will be necessary to use mechanical processes to prepare the surface, as well as chemical means to clean metal surfaces.
- Wait until the total evaporation of this cleaning water or check the support moisture.
- Before applying, take into account the residual humidity from cleaning, that is, wait until its total evaporation or verify any humidity in the surface using a measuring device.
- You can use DESMOSOLVENT(max.5 % dilution). Mix for 2 minutes, or until achieving a correct mixture
- Apply one or more coats (depending on support conditions) of PRIMER PU-1000 until the desired thickness is obtained.
- If the surface to be treated is very uneven, apply an initial coat of PRIMER PU-1000 mixed with mineral filings to level it.
- Wait until completely dry before applying the desired waterproofing or concrete protection system.

HANDLING AND TRANSPORT

These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product(MSDS) or contact our technical department.



PROPERTIES

PROPERTIES	RESULT
Density at 23 °C ISO 1675	1,11 g/cm ³
Viscosity at 23 °C ISO 2555	±120 cps
Solids content ISO 1768	>80%
VOC(volatile organic compounds)	270 g/l
Adhesion to concrete	> 2 MPa
Drying time at 23 °C	±60 minutes
Final dry time at 23 °C	2~3 hours
Recoat range time at 23 °C	3~24 hours
Environmental application range temperature	5~35 °C
Max. Moisture on the support	5%
Dilution	±5% DESMOSOLVENT

The values in this table are approximate and can vary depending on the situation of the support or application methodology employed

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

